

## **AAV TEST**

### **BS EN 1097-8:2009**

Standard test sand to BS EN 1097-8:2009- Determination of the polished stone value Annex A Determination of aggregate abrasion value (AAV).

Description: Washed, dried and graded Leighton Buzzard silica sand.

Particle Shape: Rounded to sub-rounded

Colour: White variety (silver grey to pale buff)

Particle Size: Between 850um and 300um

Grading: 100% passing 850µm \*  
75% min passing 600um  
25% max passing 425um  
0% passing 300um \*

\* Note: If less than 0.1% retained on an 850 um sieve and less than 0.1% passes 300um the material shall be deemed to comply with the standard

Packaging: Supplied in 25kg bags

***Manufactured, produced and processed by  
David Ball Group plc, Huntingdon Road, Bar Hill, Cambridge, CB23 8HN, United  
Kingdom  
Tel 01954 780687 Fax 01954 782912  
[www.pudlo.com](http://www.pudlo.com) [sales@pudlo.com](mailto:sales@pudlo.com)***