

Hot Test Grit / Hot Test Sand

BS 598-108: 2005

Standard test sand to BS 598-108:2005 Sand and grit for determination of the condition of the binder on coated chippings and for measurement of the rate of spread of coated chippings.

Description:

Both sand and grit are natural, washed, dried and graded Leighton Buzzard Silica Sand.

Colour:

Buff - light brown (pale straw).

Particle Size:

Sand 600 - 150 μ m.

Grit 2.36 - 600 μ m.

Grading:

Hot test sand

100% passing 600 μ m

90 - 100% retained 300 μ m

0 - 15% passing 150 μ m

(52/100 BS meshes)

Hot test grit

100% passing 2.36mm μ

90 - 100% passing 1.18mm μ

0 - 15% passing 600 μ m

(14/25 BS meshes)

Material is free from flaky particles, silt, clay and organic matter. Supplied in 25kg bags or tubs at an additional cost.