

AAV TEST

BS 812-113:1990

Standard test aggregate to BS 812-113:1990. Coarse sand to 6.1 (abrasive) and fine sand to 6.3 to measure the resistance of aggregate to surface wear (AAV).

Description:	Washed, dried and graded Leighton Buzzard Silica Sand.	
Particle Shape:	Rounded to Sub-rounded	
Colour:	White variety (silver grey to pale buff)	
Particle Size:	Coarse sand (Abrasive) to 6.1	600 – 425 um *
	Fine sand to 6.3	minus 212 um *
Grading:	COARSE SAND to 6.1	
	100% passing 850µm *	
	75% min passing 600um	
	25% max passing 425um	
	0% passing 300um *	

* Note: If less than 0.1% retained on an 850 um sieve and less than 0.1% passes 300um the material shall be deemed to comply with the standard

FINE SAND to 6.3
100% passing to 212um
75 – 100 % passing 150um

Packaging: Supplied in 25kg bags