

STANDARD TEST SAND FOR BS 598 : Part 105

Sand Patch sand in the determination of textured depth of bituminous pavements.

Description:	Natural, washed, dried and graded Leighton Buzzard Silica Sand.
Particle Shape:	Rounded to sub-rounded.
Colour:	White variety (silver/pale grey).
Particle Size:	300 - 150 μm
Grading:	100% passing 600 μm *
	90 - 100% passing 300 μm
	0 - 15% passing 150 μm *

Complies with the requirements of Section 4.1.3 of the Standard.

*Note: If less than 1% is retained on 600 μm sieve and less than 1% passes 150 μm the material shall be deemed to comply.

Material generally free from flaky particles, silt, clay and organic matter. Supplied clean and dry in 25kg bags or plastic containers to customer's requirements.